

Bearing parts, Heat treatment method of bearing parts and rolling bearing

Publication number: CN1421541

Publication date: 2003-06-04

Inventor: ISAMU OKI (JP)

Applicant: NTN CO LTD (JP)

Classification:






- International: **C21D1/78; C21D9/40; C23C8/32;
C23C8/80; F16C33/30; F16C33/62;
C21D9/36; C21D1/78; C21D9/40;
C23C8/06; C23C8/80; F16C33/30;
F16C33/62; C21D9/36; (IPC1-7): C23C8/30;
C21D9/36; C21D9/40; F16C19/00**

- European: **C21D1/78; C21D9/40; C23C8/32;
C23C8/80; F16C33/30; F16C33/62**

Application number: CN20021054319 20021129

Priority number(s): JP20010364516 20011129;
JP20020194775 20020703;
JP20020194793 20020703;
JP20020194804 20020703;
JP20020194921 20020703

Also published as:

 US2005205163 (A)
 US2003123769 (A)
 KR20030044797 (A)
 DE10254635 (A1)
 CN1304625C (C)

Report a data error here

Abstract not available for CN1421541

Abstract of corresponding document: **DE10254635**

The steel of the component is carbonitrided at a temperature exceeding the A1 transition temperature, then cooled below it. The steel is re-heated to a hardening temperature (T2), no less than the A1 transition temperature, but less than the carbonitriding temperature. The steel is hardened. Preferred

Features: The steel is hardened at a temperature of 790-830 deg C. Steel composition Steel remote from the hardened area contains, all on a wt. % basis: 0.6-1.2 C, 0.15-1.11 Si and 0.3-1.5 Mn. Under 2 wt. % Cr is included. Hydrogen content is below 0.5 ppm. The component includes a carbonitrided layer and austenitic grains exceeding a JIS Grain Size of No. 10. An Independent claim is included for a bearing component with austenitic grains of mean size not exceeding 8 microns .



[19] 中华人民共和国国家知识产权局

[51] Int. Cl.

C23C 8/30

G21D 9/36 G21D 9/40

F16C 19/00



[12] 发明专利申请公开说明书

[21] 申请号 02154319.4

[43] 公开日 2003 年 6 月 4 日

[11] 公开号 CN 1421541A

[22] 申请日 2002.11.29 [21] 申请号 02154319.4

[30] 优先权

[32] 2001.11.29 [33] JP [31] 2001-364516

[32] 2002.7.3 [33] JP [31] 2002-194775

[32] 2002.7.3 [33] JP [31] 2002-194793

[32] 2002.7.3 [33] JP [31] 2002-194804

[32] 2002.7.3 [33] JP [31] 2002-194921

[71] 申请人 NTN 株式会社

地址 日本大阪府

[72] 发明人 大木力

[74] 专利代理机构 上海专利商标事务所

代理人 顾峻峰

权利要求书 2 页 说明书 16 页 附图 7 页

[54] 发明名称 轴承部件、轴承部件的热处理方法
以及滚动轴承

[57] 摘要

本发明公开了一种具有较长抗滚动接触疲劳寿命、良好的抗裂强度以及老化尺寸变化受到限制的轴承部件、该轴承部件的热处理方法以及一种包括所述轴承部件的滚动轴承。用于轴承部件(1、2、3)的钢在超过 A_1 相变温度的碳氮共渗温度(T_1)经过碳氮共渗。钢被再加热到淬火温度(T_2)该温度不低于 A_1 相变温度但低于碳氮共渗温度,而后再进行淬火。

